

TetriderTM

Properties

Melting Point:	≥2100°C
Oxidation Temp. (Onset):	≥ 425°C
Hardness (Bulk):	≥43 GPa
Bulk Modulus:	339 GPa
Particle Morphology:	Platelet-like
Aspect Ratio:	≥1

